



# OneChoice™

A Universal Ancillary Brand

## OC-4

### Cut-in-Clear

#### SCA400 Cut-in-Clear

SCA400 Cut-in Clear is a 1K, fast drying clearcoat designed for use in door jambs, under hoods, under deck lids, cut-ins and spray-out cards.

SCA400 is conveniently packaged in an aerosol container, is easy to apply and provides excellent gloss.



#### Features

- Easy to use
- Convenient
- High Gloss
- Quick Dry

#### Advantages

- Increases efficiency
- “Spray gun” quality repair

#### Benefits

- Consistent results
- Proven technology

#### Required Products

- SCA400 Cut-in Clear

#### Related Products

- Recommended PPG and Nexa brand clears and topcoats.

#### Compatible Products

SCA400 Cut-in-Clear is for universal use with PPG and Nexa Brand topcoats and clears.

*Note: When using SCA400 Cut-in-Clear with recommended PPG/Nexa clears and topcoats, please refer to the product's specific technical bulletin for proper application.*

***Note: SCA400 is designed for use in areas that will not be exposed to direct sunlight.***

#### Preparation of Substrate



- In all cases, wash all surfaces to be painted with soap and water, then apply the appropriate systems cleaner. Ensure that the substrate is thoroughly cleaned and dried both before and after application work.
- When applying over existing finishes, wet sand with U.S. 500 – 600 European P800 – 1200 grade paper or dry sanding with U.S. 400 – 500 / European P600 – 800 grade paper.
- Wash off residue and dry thoroughly before recleaning with appropriate systems substrate cleaner. The use of a tack rag is recommended.
- Apply SCA400 Cut-in-Clear.
- When applying SCA400 over topcoat systems, please refer to the system's specific technical bulletin for proper application.



## Application Data

### Application:



SCA400 is ready-to-Spray.  
Using the techniques below will ensure a proper blend.

- Shake aerosol for 1 – 2 minutes to ensure contents are uniformly mixed
- Apply 2 – 3 medium – wet coats
- 5 minute flash between coats

For additional information, follow the recommended spot/panel repair procedure described in the specific Product Information Bulletin for the product(s) to be blended.

### Dry Times:

Dust time:	12 minutes
Dry to Handle:	35 minutes

### Technical Data:

Color:	Clear (Aerosol)
VOC Regulatory (Less Water Less Exempts)	5.55 lbs/gal (666 g/L)
Density:	9.27 lbs/gal
Flashpoint (PMCC):	-2°F (-19°C)

### Important:

Before opening the packages, be sure you understand the warning messages on the labels of all components, since the mixture will have the hazards of all its parts. Improper spray technique may result in a hazardous condition. Follow spray equipment manufacturer's instructions to prevent personal injury or fire. Follow directions for respirator use. Wear eye and skin protection. Observe all applicable precautions.

#### Tips:

- Do spray product in properly vented areas.
- Do use the appropriate NIOSH/MSHA respirator. Consult product label for details.
- Do shake for one minute after mixing ball rattles and spray a small area to test product before starting the job.
- Do turn the container over and spray to clear the nozzle after spraying is completed.

#### Precautions:

- Do not leave or store containers in direct sunlight. Normal storage temperature is 50°F – 100°F (10°C – 38°C).
- Do not incinerate container, contents under pressure.

**See material Safety Data Sheet and Labels for additional safety information and handling instructions.**

EMERGENCY MEDICAL OR SPILL CONTROL INFORMATION (412) 434 -4515. IN CANADA (514) 645-1320

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public. Products mentioned may be hazardous and should only be used according to directions, while observing precautions and warning statements listed on label. Statements and methods described are based upon the best information and practices known to PPG Industries. Procedures for applications mentioned are suggestions only and are not to be construed as representations or warranties as to performance, results, or fitness for any intended use, nor does PPG Industries warrant freedom from patent infringement in the use of any formula or process set forth herein.

## PPG Industries

*World Leaders in Automotive Finishes*

PPG Industries  
19699 Progress Drive  
Strongsville, OH 44149  
1-800-647-6050

PPG Canada Inc.  
2301 Royal Windsor Drive  
Mississauga, Ontario, Canada L5J 1K5  
1-888-310-4762